

97-200 Underfloor preservation

The vehicle underside should be given a corrosion protection treatment once a year, the summer months would be best. Clean vehicle underside prior to waxing.

In the course of these jobs, repair possible damage on permanent underfloor protection, as well as paint damage on bottom edges of doors, wheelhouse edges and at entrance.

Spray preservation wax on **dry** underfloor.

Do not spray with preservation wax (cover, whenever possible):

- Brake linings and brake disks. Wax-soaked brake linings must be renewed.
- Exhaust line and muffler
- Universal shafts

After repairs following accidents be sure to preserve underfloor in repaired range.

Preserve spare bodies on underfloor upon completion of vehicles.

Note

For processing equipment and wax preservation compounds refer to 97-100.